



Okehampton Business Park
Exeter Road
Okehampton
Devon EX20 1UB
Telephone: 01837 54446
Fax: 01837 54544
Web: www.elementalmicroanalysis.com

Certificate of Analysis
Part No. B2385
Carbon & Sulphur in Limestone
Standard

Certificate Number 920G
Page 1 of 1

%Carbon
Mean = 11.59
Standard Deviation = ± 0.16
Expanded Uncertainty = ± 0.34
(k=2, @95% confidence)(n=39)

%Sulphur
Mean = 0.40
Standard Deviation = ± 0.02
Expanded Uncertainty = ± 0.04
(k=2, @95% confidence)(n=39)

The intended use is for Carbon and Sulphur determination in limestone or other similar matrix materials using induction and resistance type oxygen combustion furnaces with infrared detection systems. Accelerants like Tungsten Tri-oxide (WO₃) were used in the resistance furnace. Tungsten metal and iron chip accelerators were used in the induction analysis.

Method of analysis ASTM E1915-13 and ARI-LAB-621.

Reference Materials Employed for traceability:

NCS	DC60119
EURO	ECISS 701-1
NIST	SRM 1d

ALPHA – AR4024-101602, AR4017-420R, AR4023-100902, AR4017-313B, AR4012-52199

The mean analytical values were derived by data sets showing traceability to the above-mentioned reference standards and reported in mass fraction. The mean and uncertainty values are derived under the guidance of ISO Guide 35, the Guide to Uncertainty Measurement, and ANOVA. Metrological traceability is to the SI derived unit of mass fraction expressed as percent. Refer to your test method or instrument manufacturer for the expanded method derived uncertainty if needed. When necessary, professional judgment is applied toward consideration of data and statistical information.

Sample size and minimum sample size used for this data was 150-350mg nominal. Refer to your instrument manufacturer for typical sample analysis size. This bottle contains 25g of fine powder to be used directly from the bottle without preparation. Keep tightly sealed and store under normal laboratory conditions. While unable to determine a definite shelf life this reference should be reviewed 20 years from certification.

The material used in production of this standard was sampled in accordance with ARI-LAB-603. The samples for round robin testing were selected in accordance with ARI-LAB-625. The above values relate only to the material used to produce this standard. Remedies for any claimed defect in this product will be limited to product replacement or refund of the purchase price. In no event, shall Elemental Microanalysis Ltd be liable for incidental or consequential damages. This certificate cannot be reproduced except in its entirety.

This Reference Material (RM) is traceable to the above-mentioned standards. For good laboratory practice it is recommended that all standards be verified as fit for purpose prior to use.

Certified March 16, 2021

Elemental Microanalysis Ltd