

Okehampton Business Park Exeter Road Okehampton Devon EX20 1UB Telephone 01837 54446/7 Fax 01837 54544

## Certificate of Analysis Part No. B1510 Carbon & Sulphur Iron Standard

Certificate Number 717A Page 1 of 1

% Carbon
Mean = 0.0007
Standard Deviation = +/- 0.0002
Expanded Uncertainty = +/- 0.0004
(k=2, @ 95% confidence limit) (n=59)

%Sulphur
Mean = 0.0011
Standard Deviation = +/- 0.0003
Expanded Uncertainty = +/- 0.0006
(k=2. @ 95% confidence limit) (n=59)

Method of analysis is ASTM E 1019-11 and ARI 033

Primary (NMI) / Guide 34 Reference Standards Employed:

NIST SRM 2168, 348a JSS 1205-2, 1201-4, BAM/BCS 270-1, 260/4

NCS HC11011, HC15002F ALPHA AR673-716C, AR673-814H

## Notes

The intended use of this reference standard is for the calibration and validation of induction combustion Carbon/Sulphur analysis by infra-red detection as described by ASTM E-1019. The mean analytical values were derived from 6 data sets showing trace-ability to the above mentioned primary reference standards, and reported in mass fraction. The minimum and typical size for testing was 1g (1 pin) per ASTM E1019. The precision values represent the mean value and estimated uncertainty derived from the data sets and may not represent your testing capabilities. Refer to your test method for the additional uncertainty information.

The material used in production of this standard was sampled in accordance with ARI 032. The samples used for round robin testing were selected in accordance with ARI 014. The above values relate only to the material used to produce this standard. This bottle consists of 454g iron chip to be used directly from the bottle with no preparation needed. While unable to determine a definite shelf life, this reference should be reviewed every 25 years from the date of certification. Keep sealed and store under normal laboratory conditions.

Remedies for any claimed defect in this product will be limited to product replacement or refund of the purchase price. In no event shall Elemental Microanalysis Ltd be liable for incidental or consequential damages.

This is a Certified Reference Material (working reference standard) and is trace-able to the abovementioned standards. For good laboratory practice it is recommended that all standards be verified prior to use.

Elemental Microanalysis Limited

Certified March 6, 2018