

Elemental Microanalysis Limited

Okehampton Business Park
Exeter Road
Okehampton
Devon EX20 1UB
Telephone 01837 54446/7
Fax 01837 54544

**Certificate of Analysis
Part No. B2521
Carbon & Sulphur Pin Standard**

Certificate Number 817E
Page 1 of 1

% Carbon**Mean = 0.0236****One Sigma Standard Deviation = +/- 0.0014****Expanded Uncertainty = +/- 0.0028****(k=2, @ 95% confidence limit) (n=39)****%Sulphur****Mean = 0.0246****One Sigma Standard Deviation = +/- 0.0007****Expanded Uncertainty = +/- 0.0014****(k=2, @ 95% confidence) (n=39)**

Method of analysis is ASTM E 1019-11 and ARI 033

Primary (NMI) / Guide 34 Reference Standards employed:

NIST	20g, 339, 125b, 19h, 2159, 348a, 152a
JSS	151-18, 150-15
JK	12A

ALPHA - AR881-317C, AR891-1015A, AR870-1216A, AR884-1114C

The intended use of this reference standard is for the calibration and validation of induction combustion Carbon/Sulphur analysis by infra-red detection as described by ASTM E-1019. The mean analytical values were derived by 4 data sets, showing trace-ability to the above mentioned primary reference standards, and reported in mass fraction. The minimum and typical size for testing was 1g (1 pin) per ASTM E1019. The precision values represent the estimated uncertainty derived from the data sets and may not represent your testing capabilities. Refer to your test method for additional uncertainty information.

The material used in production of this standard was sampled in accordance with ARI 032. The samples used for round robin style testing were selected in accordance with ARI 014. The above values relate only to the material used to produce this standard. This bottle consists of 454g, 1g pins (nominal weight) to be used directly from the bottle with no preparation needed. This standard has an indefinite shelf life. Keep sealed and store under normal laboratory conditions.

Remedies for any claimed defect in this product will be limited to product replacement or refund of the purchase price. In no event shall Elemental Microanalysis Ltd be liable for incidental or consequential damages.

This is a Certified Reference Material (working reference standard) and is traceable to the above-mentioned standards. For good laboratory practice it is recommended that all standards be verified prior to use.

Certified September 26, 2017

Elemental Microanalysis Limited