

Dried Basis Values

Proximate Analysis		n=	k=	ASTM	Ultimate Analysis		n=	k=	ASTM
%Ash	19.33 ± 0.26	20	2.09	D3174/D7582	%Carbon	65.03 ± 0.71	8	2.36	D5373
%Volatile Matter	30.37 ± 1.02	20	2.09	D3175/D7582	%Hydrogen	4.38 ± 0.16	8	2.36	D5373
%Fixed Carbon (calculated)	(50.30)	D3172	%Nitrogen	1.23 ± 0.14	8	2.36	D5373
%Sulphur	3.04 ± 0.08	28	2.05	D4239	%Oxygen (calculated)	(6.99)	D3176
Btu/lb	11571 ± 38	8	2.36	D5865	MAF/DAF BTU (calculated)	(14343)	D3180
Mineral Analysis		n=	k=	ASTM	Sulphur forms		ASTM		
%Silica	48.53 ± 4.23	8	2.36	D4326/D6349	%Pyritic	(1.03)	D2492		
%Alumina	24.10 ± 1.57	8	2.36	D4326/D6349	%Organic (calculated)	(1.01)	D2492		
%Titania	1.21 ± 0.09	8	2.36	D4326/D6349	%Sulphate	(1.00)	D2492		
%Ferric Oxide	17.18 ± 1.59	8	2.36	D4326/D6349	Ash Fusion Temperature		Degrees F	Degrees F	
%Calcium Oxide	1.62 ± 0.29	8	2.36	D4326/D6349	ASTM D1857	Reducing	Oxidising		
%Magnesium Oxide	0.86 ± 0.06	8	2.36	D4326/D6349	Initial deformation	(2103)	(2515)		
%Potassium Oxide	2.57 ± 0.69	8	2.36	D4326/D6349	Softening	(2277)	(2566)		
%Sodium Oxide	(0.41)	D4326/D6349	Hemispherical	(2402)	(2592)		
%Sulphur Trioxide	(1.86)	D4326/D6349	Fluid/Final	(2510)	(2642)		
%Phosphorus Pentoxide	(0.28)	D4326/D6349					
%Strontium Oxide	(0.06)	D4326/D6349					
%Barium Oxide	(0.07)	D4326/D6349	%Chlorine	(0.144)	D4208/D6721		
%Manganese Oxide	(0.04)	D4326/D6349	%Fluorine	(0.0089)	D3761/D5987		
%Undetermined (calculated)	(1.21)						

REFERENCES USED: Sulphur - NIST SRM 2684c, 2693, FC28012c; BTU - NIST 39j(Benzoic Acid); C/H/N – Phenylalanine, EDTA; Form of Sulphur – QAR-RM-6, LQSI 140022; Mineral Analysis – NIST 634a, 2689, USGS AGV-2; Chlorine – SRM2693, 2682c; Fluorine – 1632d, SARM18.

() Indicates reference or information only value.

Notes:

The intended use of this standard is for the verification of various tests by the above-mentioned methods. Typical sample size for analytical testing and minimum size is subject to the test method and instrumentation used. The uncertainty values represent the expanded uncertainty obtained through analytical testing by the mentioned ASTM methods utilizing ANOVA, ISO Guide 35, and the Guide to Uncertainty Measurement. Metrological traceability is to the SI derived units expressed as mass fraction percent, temperature, or BTU/lb. Normal test procedures should be employed when using this standard; this includes using the reproducibility and repeatability factors of the method for establishing analytical uncertainty if needed. When necessary, professional judgment is applied toward consideration of data and statistical information

The material used in production of this standard was identified in accordance with ARI 041. The samples for round-robin testing were selected in accordance with ARI 031. The above values relate only to the material used to produce this standard. The analytical samples should be dried or corrected for moisture as per the test method you are using. This bottle contains 50g fine coal powder (-60 mesh). While unable to determine a definite shelf life this reference standard should be reviewed 20 years from the date of certification. Once opened this certificate is valid for two years. Keep sealed tight and store under normal laboratory conditions. This certificate cannot be reproduced except in full. Remedies for any claimed defect in this product will be limited to product replacement or refund of the purchase price. In no event shall Elemental Microanalysis Ltd be liable for incidental or consequential damages.

This Reference Material (RM) is traceable to the above-mentioned references. For good laboratory practice it is recommended that all standards be verified as fit for purpose prior to use.

EXPIRATION DATE: THIS CRM IS VALID FOR TWO YEARS FROM THE DATE OF OPENING

CERTIFIED May 26, 2020

Elemental Microanalysis Limited