

**Certificate of Analysis
Part No. B2407
Oxygen and Nitrogen in
Stainless Steel Pin Standard**

Certificate Number: 821D
Page 1 of 1

% Oxygen
Mean = 0.0037
Standard Deviation = ± 0.0003
Expanded Uncertainty = ± 0.0006
(k=2, @95% confidence, n=36)

% Nitrogen
Mean = 0.0569
Standard Deviation = ± 0.0014
Expanded Uncertainty = ± 0.0031
(k=2, @95% confidence, n=35)

Method of Analysis is ASTM E 1019-18, and ARI-LAB-622
Primary (NMI/Guide 34/ISO17034) Reference Materials Employed:

NIST	73c, 343a
BAM/EURO	286-1, 226-1, 227-1
NCS	NS20035b, NS11044

ALPHA – AR654-1218B, AR667-315B, AR660-317B, AR654-914G, AR654-127528310, AR654-N3161003

This reference standard is intended to be a calibration or QC validation of Oxygen and Nitrogen on inert gas fusion analysers utilizing infrared (O) and thermal conductivity (N) detection as described in ASTM E1019. The analytical sample and minimum size used for testing was 1 pin (0.5g nominal). The precision values represent the estimated mean, standard deviation, and expanded uncertainty derived from using ISO Guide 35, ANOVA, and the Guide to Uncertainty Measurement. Metrological traceability is to the SI derived unit of mass fraction expressed as percent. Refer to your test method and or your instrument manufacturer for the expanded method derived uncertainty. When necessary, professional judgment is applied toward consideration of data and statistical information.

The material used in production of this standard was identified in accordance with ARI-LAB-603. The samples for round-robin testing were selected in accordance with ARI-LAB-625. The above values relate only to the material used to produce this reference standard. This reference contains 50g, 0.5g pins (nominal), to be used directly from the bottle with no preparation. While unable to determine a definite shelf life, this reference should be reviewed 25 years from the date of certification. Keep sealed and store under normal laboratory conditions.

Remedies for any claimed defect in this product will be limited to product replacement or refund of the purchase price. In no event, shall Elemental Microanalysis Ltd be liable for incidental or consequential damages. This certificate cannot be reproduced except in full.

This RM is traceable to the above-mentioned reference materials. For good laboratory practice, it is recommended that all reference materials be verified as fit for purpose prior to use.

Certified on the 28th of October 2022

Elemental Microanalysis Ltd